



Test Report

Report No: BST200914722301CR

Date: Sep.18, 2020

Page 1 of 9

Applicant : SIGNCOMPLEX LIMITED
Address : Yijia Industrial Park, Fuqian Road, Guanlan Town, Bao'an,
Shenzhen, Guangdong, China

The following sample(s) was /were submitted and identified on behalf of the clients as:

Sample Name : CIBAY-E HIGH BAY LIGHT



Trade Name :

Sample Model :

CBE-240-AH-XXK-ZYYY; CBE-200-AH-XXK-ZYYY;
CBE-150-AH-XXK-ZYYY; CBE-120-AH-XXK-ZYYY;
CBE-100-AH-XXK-ZYYY; CBE-080-AH-XXK-ZYYY;
CBE-070-AH-XXK-ZYYY; CBE-060-AH-XXK-ZYYY;
XX: represents the color 27/30/35/40/45/50/57/60/65;
YYY: can be any number or character for commercial use;
Z: Represent control function. It can be D (0-10/PWM Dimmable) only,
S (sensor control & 0-10/PWM Dimmable)only, or blank
(no control function)

Sample Received Date : Sep.15, 2020

Testing Period : Sep.15, 2020 To Sep.18, 2020

Test Requested : Selected test (s) in the selected parts as requested by client with the RoHS 2 Directive 2011/65/EU Annex II (EU) 2015/863 as last amended by Directive (EU) 2017/2102.

Test Method : Please refer to next page(s).

Test Result : Please refer to next page(s).

Signed for and on behalf of



Tony Qian/ Approved Signatory

This report shall not be altered, increased or deleted. The results shown in this test report refer only to the sample(s) tested. Without written approval of BST, this test report shall not be copied except in full and published as advertisement. BST Chemical Lab.

Dongguan BST Testing Co., Ltd.

A1201-1204 Xinsanqi of Dongbao Road, Dongcheng District,
Dongguan, Guangdong, China

Tel: 400-8829628/ 800-9990305
Http://www.bst-lab.com E-mail: christina@bst-lab.com



Test Report

Report No: BST200914722301CR

Date: Sep.18, 2020

Page 2 of 9

Test Content:

Test Item(s)	Test Method	Reference	Unit	Limit	MDL
Cadmium(Cd)	IEC 62321-5:2013	ICP-OES	mg/kg	100	2
Lead(Pb)	IEC 62321-5:2013	ICP-OES	mg/kg	1000	2
Mercury(Hg)	IEC 62321-4:2013+AMD1:2017	ICP-OES	mg/kg	1000	2
Hexavalent Chromium(CrVI) (Metal)	IEC 62321-7-1:2015	UV-Vis	µg/cm ²	0.13	0.1
Hexavalent Chromium(CrVI) (Nonmetal)	IEC 62321-7-2:2017	UV-Vis	mg/kg	1000	8
PBBs (Next form)	IEC 62321-6:2015	GC-MS	mg/kg	1000	5
PBDEs (Next form)	IEC 62321-6:2015	GC-MS	mg/kg	1000	5
Dibutyl Phthalate(DBP)	IEC 62321-8:2017	GC-MS	mg/kg	1000	30
Butyl benzyl phthalate (BBP)	IEC 62321-8:2017	GC-MS	mg/kg	1000	30
Di-(2-ethylhexyl) Phthalate(DEHP)	IEC 62321-8:2017	GC-MS	mg/kg	1000	30
Diisobutyl phthalate (DIBP)	IEC 62321-8:2017	GC-MS	mg/kg	1000	30

PBBs		PBDEs	
Monobromobiphenyl	Hexabromobiphenyl	Monobromodiphenyl ether	Hexabromodiphenyl ether
Dibromobiphenyl	Heptabromobiphenyl	Dibromodiphenyl ether	Heptabromodiphenyl ether
Tribromobiphenyl	Octabromobiphenyl	Tribromodiphenyl ether	Octabromodiphenyl ether
Tetrabromobiphenyl	Nonabromobiphenyl	Tetrabromodiphenyl ether	Nonabromodiphenyl ether
Pentabromobiphenyl	Decabromobiphenyl	Pentabromodiphenyl ether	Decabromodiphenyl ether

This report shall not be altered, increased or deleted. The results shown in this test report refer only to the sample(s) tested. Without written approval of BST, this test report shall not be copied except in full and published as advertisement. BST Chemical Lab.

Dongguan BST Testing Co., Ltd.

A1201-1204 Xinsanqi of Dongbao Road, Dongcheng District,
Dongguan, Guangdong, China

Tel: 400-8829628/ 800-9990305

Http://www.bst-lab.com E-mail: christina@bst-lab.com



Test Report

Report No: BST200914722301CR

Date: Sep.18, 2020

Page 3 of 9

Sample Description:

No.	Description	Name
1	Plastic	Black Plastic
2	Plastic	Rubber
3	Metal	Shell
4	Metal	Screw
5	Metal	Gasket
6	Metal	Silvery Metal
7	Metal	Glass
8	Plastic	White Plastic Paper
9	Metal	Aluminum Plate
10	Plastic	Blue Plastic
11	IC	IC
12	LED	LED
13	Capacitance	Capacitance
14	Resistance	Resistance
15	Bridge Pile	Bridge Pile
16	Plastic	Black Line Outside
17	Plastic	Brown Line Skin
18	Plastic	Blue Line Skin
19	Plastic	Yellow-Green Line Skin
20	Metal	Wire Core

This report shall not be altered, increased or deleted. The results shown in this test report refer only to the sample(s) tested. Without written approval of BST, this test report shall not be copied except in full and published as advertisement. BST Chemical Lab.

Dongguan BST Testing Co., Ltd.

A1201-1204 Xinsanqi of Dongbao Road, Dongcheng District,
Dongguan, Guangdong, China

Tel: 400-8829628/ 800-9990305

[Http://www.bst-lab.com](http://www.bst-lab.com)

E-mail: christina@bst-lab.com



Test Report

Report No: BST200914722301CR

Date: Sep.18, 2020

Page 4 of 9

Test Result:

Test Item(s)	No.1	No.2	No.3	No.4	No.5
Cadmium (Cd)	N.D.	N.D.	N.D.	N.D.	N.D.
Lead (Pb)	N.D.	N.D.	N.D.	N.D.	N.D.
Mercury (Hg)	N.D.	N.D.	N.D.	N.D.	N.D.
Hexavalent Chromium (CrVI)	N.D.	N.D.	N.D.	N.D.	N.D.
PBBs	N.D.	N.D.	--	--	--
PBDEs	N.D.	N.D.	--	--	--
Dibutyl Phthalate (DBP)	N.D.	N.D.	--	--	--
Butyl benzyl phthalate (BBP)	N.D.	N.D.	--	--	--
Di-(2-ethylhexyl) Phthalate(DEHP)	N.D.	N.D.	--	--	--
Diisobutyl phthalate (DIBP)	N.D.	N.D.	--	--	--
Test Item(s)	No.6	No.7	No.8	No.9	No.10
Cadmium (Cd)	N.D.	N.D.	N.D.	N.D.	N.D.
Lead (Pb)	N.D.	N.D.	N.D.	N.D.	N.D.
Mercury (Hg)	N.D.	N.D.	N.D.	N.D.	N.D.
Hexavalent Chromium (CrVI)	N.D.	N.D.	N.D.	N.D.	N.D.
PBBs	--	--	N.D.	--	N.D.
PBDEs	--	--	N.D.	--	N.D.
Dibutyl Phthalate (DBP)	--	--	N.D.	--	N.D.
Butyl benzyl phthalate (BBP)	--	--	N.D.	--	N.D.
Di-(2-ethylhexyl) Phthalate(DEHP)	--	--	N.D.	--	N.D.
Diisobutyl phthalate (DIBP)	--	--	N.D.	--	N.D.

This report shall not be altered, increased or deleted. The results shown in this test report refer only to the sample(s) tested. Without written approval of BST, this test report shall not be copied except in full and published as advertisement. BST Chemical Lab.

Dongguan BST Testing Co., Ltd.

A1201-1204 Xinsanqi of Dongbao Road, Dongcheng District,
Dongguan, Guangdong, China

Tel: 400-8829628/ 800-9990305

Http://www.bst-lab.com

E-mail: christina@bst-lab.com



Test Report

Report No: BST200914722301CR

Date: Sep.18, 2020

Page 5 of 9

Test Item(s)	No.11	No.12	No.13	No.14	No.15
Cadmium (Cd)	N.D.	N.D.	N.D.	N.D.	N.D.
Lead (Pb)	N.D.	N.D.	N.D.	N.D.	N.D.
Mercury (Hg)	N.D.	N.D.	N.D.	N.D.	N.D.
Hexavalent Chromium (CrVI)	N.D.	N.D.	N.D.	N.D.	N.D.
PBBs	N.D.	N.D.	N.D.	N.D.	N.D.
PBDEs	N.D.	N.D.	N.D.	N.D.	N.D.
Dibutyl Phthalate (DBP)	N.D.	N.D.	N.D.	N.D.	N.D.
Butyl benzyl phthalate (BBP)	N.D.	N.D.	N.D.	N.D.	N.D.
Di-(2-ethylhexyl) Phthalate(DEHP)	N.D.	N.D.	N.D.	N.D.	N.D.
Diisobutyl phthalate (DIBP)	N.D.	N.D.	N.D.	N.D.	N.D.
Test Item(s)	No.16	No.17	No.18	No.19	No.20
Cadmium (Cd)	N.D.	N.D.	N.D.	N.D.	N.D.
Lead (Pb)	N.D.	N.D.	N.D.	N.D.	N.D.
Mercury (Hg)	N.D.	N.D.	N.D.	N.D.	N.D.
Hexavalent Chromium (CrVI)	N.D.	N.D.	N.D.	N.D.	N.D.
PBBs	N.D.	N.D.	N.D.	N.D.	--
PBDEs	N.D.	N.D.	N.D.	N.D.	--
Dibutyl Phthalate (DBP)	N.D.	N.D.	N.D.	N.D.	--
Butyl benzyl phthalate (BBP)	N.D.	N.D.	N.D.	N.D.	--
Di-(2-ethylhexyl) Phthalate(DEHP)	N.D.	N.D.	N.D.	N.D.	--
Diisobutyl phthalate (DIBP)	N.D.	N.D.	N.D.	N.D.	--

This report shall not be altered, increased or deleted. The results shown in this test report refer only to the sample(s) tested. Without written approval of BST, this test report shall not be copied except in full and published as advertisement. BST Chemical Lab.

Dongguan BST Testing Co., Ltd.

A1201-1204 Xinsanqi of Dongbao Road, Dongcheng District,
Dongguan, Guangdong, China

Tel: 400-8829628/ 800-9990305

Http://www.bst-lab.com

E-mail: christina@bst-lab.com



Test Report

Report No: BST200914722301CR


Date: Sep.18, 2020

Page 6 of 9

- Note:**
1. mg/kg= ppm
 2. N.D.= Not Detected(<MDL)
 3. MDL = Method Detection Limit
 4. -- = No Testing
 5. when Cr(VI) in a sample is detected below the $0.10 \mu\text{g}/\text{cm}^2$ LOQ (limit of quantification), the sample is considered to be negative for Cr(VI). Since Cr(VI) may not be uniformly distributed in the coating even within the same sample batch, a "grey zone" between $0.10 \mu\text{g}/\text{cm}^2$ and $0.13 \mu\text{g}/\text{cm}^2$ has been established as "inconclusive" to reduce inconsistent results due to unavoidable coating variations. In this case, additional testing may be necessary to confirm the presence of Cr(VI). When Cr(VI) is detected above $0.13 \mu\text{g}/\text{cm}^2$, the sample is considered to be positive for the presence of Cr(VI) in the coating layer. unavoidable coating variations may influence the determination Information on storage conditions and production date of the tested sample is unavailable and thus Cr(VI) results represent status of the sample at the time of testing.

Test Process:

1. Test for Cd/Pb Content



This report shall not be altered, increased or deleted. The results shown in this test report refer only to the sample(s) tested. Without written approval of BST, this test report shall not be copied except in full and published as advertisement. BST Chemical Lab.

Dongguan BST Testing Co., Ltd.

A1201-1204 Xinsanqi of Dongbao Road, Dongcheng District,
Dongguan, Guangdong, China

Tel: 400-8829628/ 800-9990305

Http://www.bst-lab.com E-mail: christina@bst-lab.com




Test Report

Report No: BST200914722301CR


Date: Sep.18, 2020

Page 7 of 9

2. Test for Hg Content



3. Test for Chromium (VI) Content



This report shall not be altered, increased or deleted. The results shown in this test report refer only to the sample(s) tested. Without written approval of BST, this test report shall not be copied except in full and published as advertisement. BST Chemical Lab.




Test Report

Report No: BST200914722301CR

Date: Sep.18, 2020

Page 8 of 9

4. Test for DBP, BBP, DEHP, DIBP, PBB, PBDE Content



This report shall not be altered, increased or deleted. The results shown in this test report refer only to the sample(s) tested. Without written approval of BST, this test report shall not be copied except in full and published as advertisement. BST Chemical Lab.

Dongguan BST Testing Co., Ltd.

A1201-1204 Xinsanqi of Dongbao Road, Dongcheng District,
Dongguan, Guangdong, China

Tel: 400-8829628/ 800-9990305

Http://www.bst-lab.com E-mail: christina@bst-lab.com




Test Report

Report No: BST200914722301CR

Date: Sep.18, 2020

Page 9 of 9

Sample Photo:



*** End of Report ***

This report shall not be altered, increased or deleted. The results shown in this test report refer only to the sample(s) tested. Without written approval of BST, this test report shall not be copied except in full and published as advertisement. BST Chemical Lab.

Dongguan BST Testing Co., Ltd.

A1201-1204 Xinsanqi of Dongbao Road, Dongcheng District,
Dongguan, Guangdong, China

Tel: 400-8829628/ 800-9990305

Http://www.bst-lab.com E-mail: christina@bst-lab.com